



# Blueskin<sup>®</sup> Primer and Blueskin<sup>®</sup> Primer Ultra

Primers for Self-Adhesive Membranes

## Physical Properties

	<b>Blueskin<sup>®</sup> Primer</b>	<b>Blueskin<sup>®</sup> Primer Ultra</b>		
-Colour	Blue	Clear amber	-Service Temp	Minus 40°C to 70°C
-Solids by Weight	35%		-Application Temp	Minus 12°C to 40°C
-Weight	0.8 kg/l (6 lbs./gal. U.S.) (approx.)		-Flammability	
-Coverage	2 to 6 m <sup>2</sup> /l (up to 250 ft <sup>2</sup> /gal. U.S.) depending on porosity and texture of surface.	3 to 5 m <sup>2</sup> /can (30 to 50 ft <sup>2</sup> /can)	Wet	Flammable
-Drying Time			Dry	Burns
Initial Set	30 minutes	3 minutes		
Set Through	2 hours	20 minutes		

## Description

**Blueskin<sup>®</sup> Primer** is a rubber based adhesive primer for self -adhesive membranes.

## Features

- Quick setting.
- Aggressive tack provides adhesion of membrane.
- Suitable for application at normal and low temperatures.
- Easily applied.

## Uses

Used as a primer for self-adhesive membranes such as **Blueskin<sup>®</sup> SA, WP200** or **RF200** when applied to masonry, concrete, wood, gypsum board, Dens Glass Gold and metal surfaces.

**Blueskin<sup>®</sup> Primer** is the primer of choice on above grade applications of self-adhered membranes where a quick setting, aggressive tack, solvent based primer is required.

**Blueskin<sup>®</sup> Primer Ultra** is ideal where a very fast drying primer is required. Convenient spray can application eliminates the need for brushes or rollers. Three minute tack time.

Designed for applications above -12°C.

## Limitations

Solvent in product attacks polystyrene insulation. Avoid use where solvent odours may taint food or other susceptible products.

## Packaging

**Blueskin<sup>®</sup> Primer** is packaged in 17L and 3.5L pails.

**Blueskin<sup>®</sup> Primer Ultra** is packaged in 425g spray cans.

### **Preparation**

---

Surfaces must be dry and free from dust, dirt, grease, oil or other foreign matter.

### **Application**

---

**Blueskin® Primer:** Apply by brush, roller or spray. Rollers should have a heavy nap of natural material such as lamb's wool. Allow Primer to dry for 30 minutes before applying membrane.

**Blueskin® Primer Ultra:** Shake can and spray. Allow to tack up for three minutes before applying membrane.

Primed surfaces not covered by membrane during the working day must be reprimed.

### **Clean Up**

---

Use mineral spirits.

### **Caution**

---

Contains extremely flammable solvents. Take suitable fire precautions. Do not allow smoking or welding in working area. Keep away from open flame or spark. Use under well ventilated conditions. Avoid prolonged breathing of vapours and repeated contact with skin. Excessive inhalation of vapours can cause dizziness. (Use respirator approved for organic vapours). Keep containers covered when not in use. Harmful if swallowed. <>